

SYSTEM TEST PERFORMANCE

Product Performance meets or exceeds approved testing standards

	Test	Method	Criteria
	Component 3000 Performance and Accelerated Weathering	ASTM G-53	No deleterious effect after 3000 hours when viewed under 5X magnification ³
	Freeze/Thaw	ASTM G-67	No deleterious effect after the 300 cycle test requirement period
	Water Resistance	Tappi T433	5+ hours
	Water Vapor Transmission	Tappi T448	Average 3+ perms
	Mildew Resistance	ASTM D-3273	No growth supported within 28 days
	Salt Spray Resistance	ASTM 8117	No deleterious effect after 300 hours
	Elongation	ASTM D-638	15%
	Adhesion	ASTM C-297	No adhesion loss
	Tensile Strength	ASTM D-638	210 psi
	One Hour Fire Wall	ASTM E1 19	One Hour ⁴
	Flame Spread	ASTM E-84	IBC Class I NFPC Class A
	Smoke Density	ASTM E-84	45-less than red oak
	Toxicity	LABC Div. 61	Passed

3. No deleterious effect = no cracking, checking, crazing, lesion, rusting, blistering, peeling or delamination.

4. When applied over one hour approved substrate.